



HI-PU 3060 POLYURETHANE TOPCOAT GLOSS

Technical Data Sheet

GENERAL DESCRIPTION

A two-component high quality acrylic-polyurethane enamel specially designed with highly durable, high gloss level and colour retention topcoat finish.

RECOMMENDED USES

HI-PU 3060 when applied over such proven priming systems, offers outstanding performance including abrasion, chemical and impact resistance and colour retention.

FEATURES

- Outstanding weather resistance
- Fast dry
- Good durability

TECHNICAL SPECIFICATION

Colour	Wide range of colour
Finish	Gloss
Theoretical Coverage	6 - 8 m ² / kg @ 50 microns DFT
Recommended Dry Film Thickness	40 - 50 microns
Drying Time	Touch dry: 30 minutes at 30°C Hard dry: 6 hours at 30°C Fully cured: 5 days at 30°C
Recoating Interval	Minimum: 6 hours at 30 °C
Thinner	PU Thinner
Mixing Ratio	Base: Hardener = 5: 1 by weight = 4: 1 by volume
Pot Life	5 hours at 30 °C
Shelf Life	12 months

The information contained herein with is accurate and reliable to our best knowledge. Therefore, no implied conditions, warranties or other terms will apply to the Product. We do not and cannot warrant the results which the user may obtain by using the product to meet any particular requirements.



HI-PU 3060 POLYURETHANE TOPCOAT GLOSS

Technical Data Sheet

APPLICATION METHOD

Brush	For normal use thinning is not usually necessary.
Roller	For normal use thinning is not usually necessary.
Conventional Air Spray	Thin with 10% of PU Thinner and adjust to requirement.
Airless Spray	Ready for use. Thinning is not usually necessary.

SURFACE PREPARATION

Surface to be painted must be dry and free from grease, dirt and other contaminants. HI-PU 3060 should always be applied over a recommended anti-corrosive primer coating for metal surface. The primer surface should be dry and free from oil and other contaminations.

STORAGE

Store in a cool, dry place away from direct sunlight.

PACKING SIZE

5L / set

The information contained herein with is accurate and reliable to our best knowledge. Therefore, no implied conditions, warranties or other terms will apply to the Product. We do not and cannot warrant the results which the user may obtain by using the product to meet any particular requirements.